

## MINING / CONSTRUCTION

# CARBOTHIX FAST

## SILICATE RESIN ANCHORING GROUT

### DESCRIPTION

CarboThix Fast is an immediate partially stiffening and very fast curing dual component silicate resin for bonding injection drilling anchors, also for rock stabilization and water sealing. CarboThix Fast was developed to improve the productivity of ground support installation in underground mining and tunnelling applications. Using the pumpable resin enables load to be taken up in minutes rather than the typical 24 hours from cementitious grouted systems. During application, the two components are intimately mixed and achieve a grease-like viscosity (the so called thix effect), so that the grout stops flowing and cures to form a tough elastic and non-porous resin that will not mix with water or be diluted in wet holes. Together they form an interpenetrating network, as a tough elastic non-porous silicate resin. The resulting viscous emulsion will not take up any additional water (from the rock), will not mix with water and is resistant to dilute acids and alkalis as well as fats. As the system is under pump pressure, some grout is pushed into minor cracks and fissures around the anchor hole, ensuring full encapsulation of the anchor. As the two resin components are mixed at a set volume, consistent mixing of the grout is guaranteed, an advantage over cementitious grouts. This delivers a reliable quality of grout and anchoring performance. Operator safety and handling issues are also improved over cementitious grouting systems

### USES

CarboThix Fast was developed to improve the productivity of ground support installation in underground mining and tunnelling applications. The thixotropic nature of the grout as well as its resistance against water provide a unique sealing against pressurized water inflow. Typical applications of CarboThix Fast include grouting of cable bolts, steel or GFRP bolts, and sealing of roof bolts.



### ADVANTAGES

- Full encapsulation of anchors
- Immediate loading capacity of the bolt
- Long distance pumping (up to 1500 ft)

### APPLICATION METHOD

After thoroughly mixing the two components, the resin instantly achieves a grease-like viscosity level so that the mix stops flowing, even in large fissures, and requires pump pressure for displacement. The components are to be pumped at the volumetric ratio of 1:1 by using a dual component pump with final mixing of the materials achieved at the wand via a static mixer prior to placement. CarboThix's high strength, provides a uniform transfer of local rock stresses over the whole length of the bolt.

For bonding of injection anchors (SDA's, and hollow bar), the mixed resin is injected into the drilled hole to the maximum depth to fill the annular space and adjacent joints. For detailed instructions on use (particularly before a change of injection resins), consult the Minova "Technical handbook for the safe use of injection resins within the mining sector".

**TECHNICAL DATA**

The data below is laboratory data. Results may vary in practice due to thermal exchange between resin and strata, surface properties of the rock, humidity, pressure, and other factors.

**MATERIAL DATA**

Parameter	Unit	Component A	Component B
Density at 77°F (25 °C)	kg/m <sup>3</sup>	1430 ± 50	1160 ± 50
Color		light brown	dark brown
Flash point	°F	N/A	>212
Viscosity at 77°F (25 °C)	cps	300 - 420	150 - 230

**REACTION DATA**

Initial Temperature	77°F (25°C)
Solidification Time	1 min – 1 min 30 sec

**SAFETY INSTRUCTIONS AND LIMITATIONS**

This product is designed, manufactured and sold specifically and exclusively for use in drilled boreholes in underground mining and tunneling applications. Any use of this product in wet open air outside of a fully encircled borehole is at the user’s sole risk and responsibility and Minova USA, Inc. disclaims all liability.

**STORAGE AND SHELF LIFE**

At least 12 months from date of manufacture when stored in a dry place. If this time is exceeded, we recommend having the material checked by Minova USA, Inc. for compliance with specification. Instruction on storage conditions must be observed. Please see Safety Data Sheet (SDS) recommendations for product handling and storage.

**PACKAGING AND TRANSPORTATION**

CONTAINER TYPE	CARBOTHIX FAST COMPONENT A	CARBOTHIX FAST COMPONENT B
PC (Jug)	77 lbs (35 kg)	66 lbs (27 kg)
Steel Drum	614 lbs (278 kg)	529 lbs (240 kg)
IBC (Tote)	3,069 lbs (1392 kg)	2,435 lbs (1,104 kg)

Other packing units available on request.

**DISPOSAL**

If this product as supplied becomes a waste, it does not meet the criteria of a hazardous waste as defined under the Resource Conservation and Recovery Act (RCRA) 40 CFR 261. Dispose of material in accordance with all applicable federal, state/provincial and local laws and regulations. Regulations may vary in different locations. Waste characterizations and compliance with applicable laws are the responsibility solely of the waste generator.

**APPROVALS AND CERTIFICATES**



an ISO 9001:2015  
Quality Management System Certified Company.

**DISCLAIMER**

© 2021 Minova. All rights reserved. All information contained in this document is provided for informational purposes only and is subject to change without notice. Since Minova cannot anticipate or control the conditions under which this information and its products may be used, each user should review the information in the specific context of the intended application. To the maximum extent permitted by law, Minova specifically disclaims all warranties express or implied in law, including accuracy, non infringement, and implied warranties of merchantability or fitness for a particular purpose. Minova specifically disclaims, and will not be responsible for, any liability or damages resulting from the use or reliance upon the information in this document.

The word Minova and the associated image are registered trademarks.

**ADDITIONAL DOCUMENTATION**

Started more than 135 years ago, Minova is a global manufacturer and supplier of chemical and mechanical earth control products and support equipment. With manufacturing plants on five continents and operations in more than 25 countries, Minova is an industry-leading provider of ground support solutions for the underground mining, construction and energy industries.

If further information is required consult Minova Americas website: [www.minovaglobal.com](http://www.minovaglobal.com).

- CarboThix Fast Component A Safety Data Sheet (SDS)
- CarboThix Fast Component B Safety Data Sheet (SDS)
- Minova Technical Handbook for the Safe Use of Injection Resins within the Mining Sector
- CarboThix Product Brochure
- Minova Field Manual – Handling Injection Resins in Tunneling and Civil Engineering
- Minova CarboThix Product Specification

**MANUFACTURER**

Trading Name:  
Minova USA, Inc.  
150 Summer Court  
Georgetown, KY 40324

**CUSTOMER SERVICE**

[Customer.salessupport@minovaglobal.com](mailto:Customer.salessupport@minovaglobal.com)  
Phone: +1 (800) 626-2948  
Alt Phone: +1 (502) 863-6800  
Fax: +1 (502) 863-6805